

Amendments to the Claims:

1. (Currently Amended) Polysaccharide double-layer microcapsules constituted by an outer layer of chitosan and an inner layer of alginate wherein they are obtained:

- from solutions of alginate with initial concentrations ranging from 2 to 4% w/v comprising the further polymer hydroxypropylmethylcellulose at the initial concentration of 0.4% w/v;
- from solutions of chitosan with initial concentrations ranging from 0.1 to 0.5% w/v;
- from solutions of divalent ions with concentrations of 0.5% w/v, when the divalent ion functions as a gelification agent of the alginate to form single-layer capsules of alginate encapsulating at least one biologically active substance, and ranging from 10 to 15% w/v when the divalent ion has a stabilizing function of the double layer capsules microcapsule's outer coating of chitosan;

wherein said at least one biologically active substance is lysozyme;

for use as carriers for the oral administration of said biologically active substances.

2. (Cancelled)

3. (Currently Amended) Polysaccharide double-layer microcapsules as claimed in claim 1, wherein the initial concentration of alginate is 4% w/v, the initial concentration of chitosan is 0.1% w/v and the divalent ion with stabilizing function on the double layer microcapsules microcapsule's outer coating of chitosan has an initial concentration of 15% w/v.

4. (Original) Polysaccharide double-layer microcapsules as claimed in claim 1, wherein the divalent ion is calcium.

5. (Currently Amended) Polysaccharide double-layer microcapsules as claimed in claim 1, wherein said lysozyme is an adjuvant, and further comprising at least one the biologically active substance substances are selected from the group consisting of immunomodulants, antigens, chemotherapeutics, cytokines and growth factors.

6-28 (Cancelled)

29. (Currently Amended) Polysaccharide double-layer microcapsules constituted by an outer layer of chitosan and an inner layer of alginate wherein they are obtained through:

a) formation of single-layer capsules encapsulating at least one biologically active substance starting from solutions of alginate in concentrations ranging from 2 to 4% w/v comprising the further polymer hydroxypropylmethylcellulose at the initial concentration of 0.4% w/v, in which said substance is dispersed, by gelification with a solution of a divalent ion at a concentration of 0.5% w/v;

b) formation of the second coating layer of chitosan and stabilization of the double-layer microcapsule obtained by adding a solution of chitosan in concentrations ranging from 0.1 to 0.5% w/v and containing a divalent ion in concentrations ranging from 10 to 15% w/v in the solution containing the single-layer capsules of alginate encapsulating said substance obtained in a);

wherein said at least one biologically active substance is lysozyme;

for use as carriers for the oral administration of said biologically active substances.

30. (Cancelled)

31. (Previously Presented) Polysaccharide double-layer microcapsules as claimed in claim 29, wherein the initial concentration of alginate is 4% w/v, the initial concentration of chitosan is 0.1% w/v and the divalent ion with stabilizing function on the double layer microcapsules has an initial concentration of 15% w/v.

32. (Previously Presented) Polysaccharide double-layer microcapsules as claimed in claim 29, wherein the divalent ion is calcium.

33. (Currently Amended) Polysaccharide double-layer microcapsules as claimed in claim 29, wherein said lysozyme is an adjuvant, and further comprising at least one the biologically active substance ~~substances~~ are chosen from the group consisting of immunomodulants, antigens, chemotherapeutics, cytokines and growth factors.

34-36 (Cancelled)

37. (Withdrawn) A method for vaccinogenic or therapeutic treatment for the prophylaxis and therapy of infectious or non-infectious diseases by administering to a mammal, human or not human, in need a pharmaceutical composition comprising polysaccharide double-layer microcapsules constituted by an outer layer of chitosan and an inner layer of alginate obtained:

- from solutions of alginate with initial concentrations ranging from 2 to 4% w/v comprising the further polymer hydroxypropylmethylcellulose at the initial concentration of 0.4% w/v;

- from solutions of chitosan with initial concentrations ranging from 0.1 to 0.5 % w/v;

- from solutions of divalent ions with concentrations of 0.5% w/v, when the divalent ion functions as a gelification agent of the alginate to form single-layer capsules of alginate encapsulating at least one biologically active substance, and ranging from 10 to 15% w/v when the divalent ion has a stabilizing function of the double layer capsules.

38. (Cancelled)

39. (Withdrawn) The method as claimed in claim 37, wherein the initial concentration of alginate is 4% w/v, the initial concentration of chitosan is 0.1% w/v and the divalent ion with stabilizing function on the double layer microcapsules has an initial concentration of 15% w/v.

40. (Withdrawn) The method as claimed in claim 37, wherein the divalent ion is calcium.

41. (Withdrawn) The method as claimed in claim 37, wherein the biologically active substances are chosen from immunomodulants, antigens, chemotherapeutics, cytokines and growth factors.

42. (Withdrawn) The method as claimed in claim 37, wherein the biologically active substance is lysozyme.

43. (Withdrawn) The method as claimed in claim 37, wherein an adjuvant is associated with the biologically active substance to increase the biological response.

44. (Withdrawn) The method as claimed in claim 43, wherein the adjuvant is lysozyme.

45. (Withdrawn) The method as claimed in claim 37, wherein the prophylaxis and therapy of infectious or non-infectious diseases is applied in the animal breeding or fish farming field.

46. (Withdrawn) The method as claimed in claim 37, wherein the composition of polysaccharide double-layer microcapsules are in formulations suitable for oral administration selected from solid forms consisting of powders, tablets, capsules, or liquid forms consisting of

oily or aqueous solutions, both for multiple dosage and in single doses with excipients or diluents acceptable from the pharmaceutical and feeding purposes in the human and veterinary field.

47. (Withdrawn) Process for preparation of polysaccharide double-layer microcapsules constituted by an outer layer of chitosan and an inner layer of alginate comprising the following phases:

a) formation of single-layer capsules encapsulating at least one biologically active substance starting from solutions of alginate in concentrations ranging from 2 to 4% w/v comprising the further polymer hydroxypropylmethylcellulose at the initial concentration of 0.4% w/v, in which said substance is dispersed, by gelification with a solution of a divalent ion at a concentration of 0.5% w/v;

b) formation of the second layer of chitosan and stabilization of the double-layer microcapsule obtained by adding a solution of chitosan in concentrations ranging from 0.1 to 0.5% w/v and containing a divalent ion in concentrations ranging from 10 to 15% w/v in the solution containing the single-layer capsules of alginate encapsulating at least one biologically active substance obtained in a).

48. (Withdrawn) Process for preparation of polysaccharide double-layer microcapsules as claimed in claim 47, wherein added to phases a) and b) is the phase c) of dehydration, isolation and drying of the microcapsules obtained.

49. (Cancelled)

50. (Withdrawn) Process for preparation of polysaccharide double-layer microcapsules as claimed in claim 47, wherein the initial concentration of alginate is 4% w/v, the initial concentration of chitosan is 0.1% w/v and the divalent ion with stabilizing function on the double layer microcapsules has an initial concentration of 15% w/v.

51. (Withdrawn) Process for preparation of polysaccharide double-layer microcapsules as claimed in claim 47, wherein the divalent ion is calcium.

52. (Withdrawn) Process for the preparation of microcapsules as claimed in claim 47, wherein the biologically active substances are chosen from immunomodulants, antigens, chemotherapeutics, cytokines and growth factors.

53. (Withdrawn) Process for the preparation of microcapsules as claimed in claim 47, wherein the biologically active substance is lysozyme.

54. (Withdrawn) Process for preparation of polysaccharide double-layer microcapsules as claimed in claim 47, wherein an adjuvant is associated with the biologically active substance to increase the biological response.

55. (Withdrawn) Process for preparation of polysaccharide double-layer microcapsules as claimed in claim 54, wherein the adjuvant is lysozyme.